

WINGERTER LABORATORIES, INC.

Engineering Testing & Inspection Services
1820 N.E. 144 Street, North Miami, FL 33181
Telephone (305) 944-3401 Fax (305) 949-8698

REPORT OF TESTING

CLIENT:	Blue World Crete, Inc.	REPORT NO:	1
PROJECT:	Quality Control 2011	ORDER NO:	11-1230
LOCATION:	Wingerter Laboratories Inc., North Miami, Fl	PAGE NO.:	1 of 1

Sample Description: Geo-Blue Crete II

Hydrochloric Acid 0.2N

1	1410.0	1393.2	1.2%
2	*	*	*
3	1585.5	1567.8	1.1%

Start Soak 8/24/2011 9:00AM
End Soak 8/26/2011 3:00 PM

Total Time 54 Hrs

* Sample broke apart while drying prior to soak

Note: ASTM D 543 requires 120 hr soak time, therefore this test does not produce the findings normally produced by this test. However - due to the relatively small amount of loss during the soaks, this material can be assumed to be of passing composition to a 0.2N Hydrochloric Acid soak.
